

Dimensjonstoleranser for varmvalset bolt fra Ovako

EN 10060

I tabellen er det brukt egenvekt
 7,85 kg/dm³

Diameter mm	Toleranse mm	Toleranse mm	Vekt kg/m	Flateareal cm ²
14	± 0,4	± 0,20	1,21	1,54
15	± 0,5		1,39	1,77
16			1,58	2,01
18			2,00	2,54
19			2,23	2,84
20			2,47	3,14
22		2,98	3,80	
24	± 0,6	± 0,25	3,55	4,52
25			3,85	4,91
26			4,17	5,31
27			4,49	5,73
28			4,83	6,16
30			5,55	7,07
32	± 0,8	± 0,30	6,31	8,04
35			7,55	9,62
36			7,99	10,2
38			8,90	11,3
40			9,86	12,6
42			10,9	13,9
45	± 1	± 0,40	12,5	15,9
48			14,2	18,1
50			15,4	19,6
52			16,7	21,2
55			18,7	23,8
60			22,2	28,3
63	± 1,3	± 0,50	24,5	31,2
65			26,0	33,2
70			30,2	38,5
73			32,9	41,9
75			34,7	44,2
80			39,5	50,3
85	± 1,5	± 0,60	44,5	56,7
90			49,9	63,6
95			55,6	70,9
100			61,7	78,5
105			70,0	86,6
110			74,6	95,0
115	± 2	± 0,70	81,5	10,0
120			88,8	113,0
125			96,3	123,0
130			104,0	133,0
135			112,0	143,0
140			121,0	154,0
145	± 2	± 0,80	130,0	165,0
150			139,0	177,0
155			148,0	189,0
160			158,0	201,0
165			168,0	214,0
170			178,0	227,0
175	± 2,5	± 0,90	189,0	241,0
180			200,0	254,0
190			223,0	284,0
200			247,0	314,0

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20