



Product Guide

POLYCASA XT

POLYCASA XT IS OUR MOST WIDELY USED SHEET AND IS PERFECT FOR RETAIL, MAGAZINE SHELVING AND LIGHTING CONTROLLERS.

With sparkling clarity and the ability to be formed into shapes that blend into a store layout, you hardly notice it: the material does its job without distracting from the products being displayed. And when used in the sign industry, XT provides long lasting UV resistant signs — so your products get the promotion they deserve.



PRODUCT IDENTIFICATION

XT is one of the trade names of **Polycasa** for extruded acrylic (polymethylmethacrylate PMMA) in the form of large dimensional sheets.

Offering solutions to both indoor and outdoor applications, **Polycasa XT** is available in clear and opal white standard, and in a wide range of colours and designs.

Sheets are produced and tested according to DIN EN ISO 7823-2.

CHARACTERISTICS

- Good optical properties — brilliant transparency showing excellent colour.
- High-quality surfaces — very good weathering and ageing resistance.
- Can be used in contact with foodstuffs — meets all current European food control legislation.
- Does not contain any toxic materials or heavy metals which may cause environmental damage or health risks.
- Easy to recycle.
- High impact grades **Polycasa XT610**, **XT620** and **XT630** have outstanding mechanical properties and excellent impact strength.

APPLICATIONS

- Construction components: light domes, partition walls, glazing, roofing, caravan windows.
- Lighting: prismatic control lenses, opal diffusers.
- Engineering components: housings, machine covers.
- Advertising and decoration: letters, shop fittings, panels, Point Of Purchase displays.
- Other applications: containers, lettering templates, solariums UVT (UV-transmitting grade).

PRODUCT RANGE

- Available with anti-reflex, opal and opaque features.
- Standard range of thickness is from 1.5 to 25 mm.
- Colours: clear, white, glossy black, brown, silicate green.
- Standard sheet dimensions are 3050 x 2050 mm (sheets of 2050 x 1250 mm are also available, subject to special conditions).
- Special products: **Polycasa XT Soft Tone**, **Polycasa XT High Impact** and **Polycasa XT UV transmitting**.
- Special thicknesses, colours and patterns can be produced to order, subject to conditions.

Please contact your local customer service centre for a complete product overview. For details see back of brochure.

TECHNICAL INFORMATION

GENERAL						
Property	Method	Units	XT	XT 630	XT 620	XT 610
Density	ISO 1183	g/cm ³	1.19	1.17	1.16	1.15
Water Absorption 24h/23°C-50x50x4mm ³	DIN EN ISO 62 Method 1	%	0.2	0.25	0.3	0.3
Ball indentation hardness	ISO 2039-1	MPa	235	155	135	100
Forming temperature air pressure		°C	140-160	130-150	130-150	130-150
Forming temperature vacuum		°C	160-190	140-170	140-170	140-170
Moulding shrinkage		%	0.5-0.8	0.6-0.9	0.6-0.9	0.6-0.9
MECHANICAL						
Property	Method	Units	XT	XT 630	XT 620	XT 610
Tensile Strength	ISO 527-2	MPa	70	55	50	40
Elongation at break	ISO 527-2	%	4	15	25	35
Tensile Modulus	ISO 527-2	MPa	3200	2400	2100	1800
Flexural Strength	ISO 178	MPa	115	90	85	65
Flexural Modulus	ISO 178	MPa	3300	2400	2100	1800
Impact strength Charpy unnotched	ISO 179-1	KJ/m ²	17	25	35	60
Impact strength Charpy notched	ISO 179-1	KJ/m ²	2	3	4	5
THERMAL						
Property	Method	Units	XT	XT 630	XT 620	XT 610
Vicat Temperature (B 50)*	ISO 306	°C	105	104	102	98
Specific heat capacity	ISO 11357-4	J/gK	1.47	1.5	1.5	1.5
Linear thermal expansion	DIN 53752	K ⁻¹ *x10 ⁻⁵	7	9	10	11
Thermal Conductivity	DIN 52612	W/mK	0.18	0.18	0.18	0.18
Service temperature continuous use		°C	70	65	65	65
Max.temperature short term use		°C	90	85	80	75
Degradation temperature		°C	>280	>280	>280	>280
OPTICAL						
Property	Method	Units	XT	XT 630	XT 620	XT 610
Light transmission(3mm)	DIN 5036-3/ EN ISO 13468-2	%	92	91	91	90
Refractive Index	ISO 489	N _{D20}	1.492	1.492	1.492	1.492
ELECTRICAL						
Property	Method	Units	XT	XT 630	XT 620	XT 610
Surface Resistivity	IEC 60093	Ω	3x10 ¹⁵ - 3x10 ¹⁶	-	-	-
Volume Resistivity	IEC 60093	Ω x m	1x10 ¹³ - 5x10 ¹³	-	-	-
Electrical strength	IEC 60243-1	KV/mm	10	-	-	-
Dielectric strength	IEC 60243-1	kV/mm	30	30	30	30
Dielectrical dissipation factor 50 Hz	DIN 53483-2		0.06	-	-	-
Dielectrical dissipation factor 1 KHz	DIN 53483-2		0.04	-	-	-
Dielectrical dissipation factor 1 MHz	DIN 53483-2		0.02	0.03	0.03	0.03
Relative permittivity 50 Hz	DIN 53483-2		2.7	-	-	-
Relative permittivity 1 KHz	DIN 53483-2		3.1	-	-	-
Relative permittivity 1 MHz	DIN 53483-2		2.7	2.9	2.9	2.9

*Pre treatment 16h at 80°C

Note: The technical data of our products are typical ones; the actually measured values are subject to production variations.

For further information on the wide range of Polycasa products please contact us as follows;

UK and Ireland

T: 00 44 28 67 74 11 11

France, Italy, Greece and Cyprus

T: 00 33 385 73 68 19

Germany, Austria, Switzerland

T: 00 49 61 31 63 11 82

Spain and Portugal

T: 00 34 93 565 12 30

Central and Eastern Europe

T: 00 421 41 707 14 20 – 24

Benelux, Scandinavia and all other countries

T: 00 32 14 57 67 11

HEAD OFFICE

Polycasa

Leukaard 1

BE 2440 Geel

Belgium

T: 00 32 14 57 67 06

F: 00 32 14 58 96 21

E: info@polycasa.com

W: www.polycasa.com

Polycasa offers an extensive range of plastic sheets to distribution and industrial partners, with an industry leading selection of polymers, thicknesses, sizes, colours, patterns, and coatings.



Brands from Polycasa:



While we have made every effort to ensure the accuracy of the information it is provided on an "as is" basis and without liability, particularly including (but not limited to) liability with regard to any up to date status, completeness or correctness of the information or any liability for the merchantability of products, their fitness for any particular purpose, or the infringement of third party rights. Colours of the products are for indication purposes only and may not represent the colour of the actual product. Any opinions provided in the Product Guide are not statements or representations of fact and they are not intended to form part of any offer or contract. © Polycasa Group, 2013, all rights reserved.