

Trovidur® ET

Product characteristics

- Normal impact strength
- High transparency
- Very good printable

Product applications

- Clean room and semi conductor industry
- Mechanical engineering
- Advertising technology

	Test method	Unit	Value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,40
Water absorption	DIN EN ISO 62	%	≤0,20
Flammability (Thickness from 2 mm)	UL 94		V0
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	70
Elongation at break	DIN EN ISO 527	%	10
Tensile modulus of elasticity	DIN EN ISO 527	MPa	3200
Notched impact strength	DIN EN ISO 179	kJ / m ²	2
Shore hardness	DIN EN ISO 868	scale D	83
Thermal properties			
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	60 - 80
Service temperature, long term	Average	°C	-10 ... 55
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	67
Electrical properties			
Dielectric constant	IEC 60250		3,2
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,02
Volume resistivity	IEC 60093	Ω * cm	>10 ¹⁵
Surface resistivity	IEC 60093	Ω	>10 ¹³

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.