

Trovidur® W 1014

Product characteristics

- High chemical resistance
- Good glueability
- Weldable and hot-formable

Product applications

- Seals
- Cutting boards
- Compensators

	Test method	Unit	Value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,22
Mechanical properties			
Elongation at break	DIN EN ISO 527	%	250
Shore hardness	DIN EN ISO 868	scale A	66
Thermal properties			
Service temperature, long term	Average	°C	0 ... 60

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.